

Test time	Position of erosion front (mm)	Accumulated rain (mm)	Tangential speed at erosion front ( $\text{m s}^{-1}$ )	Kinetic energy, of each impact (J)	Impacts/area to removed coating ( $\text{cm}^{-2}$ )
(h)	(mm)	(mm)	( $\text{m s}^{-1}$ )	(J)	( $\text{cm}^{-2}$ )
0.5	66	16	131	0.036	$8.5 \times 10^3$
1.0	135	33	122	0.031	$1.6 \times 10^4$
1.5	161	49	119	0.029	$2.3 \times 10^4$
2.0	182	65	116	0.028	$3.0 \times 10^4$
2.5	208	81	112	0.026	$3.6 \times 10^4$
3.0	228	98	110	0.025	$4.3 \times 10^4$