





RevNo	Revision note	Date	Signature	Checked
-------	---------------	------	-----------	---------



4.Triaxial ($\pm 45/0$) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m²
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface le area = 0,0198 m² - Surface te area = 0,0194 m²



5.Triaxial ($\pm 45/0$) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m²
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface le area = 0,0198 m² - Surface te area = 0,0194 m²



6.Triaxial ($\pm 45/0$) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m²
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface le area = 0,1517 m² - Surface te area = 0,1636 m²

The pictures show the blade in flattened state
Fabrication method : Wet hand Lay-up
Mean Wf (fiber weight fraction) = 0.55

Itemref	Quantity	Title/Name, designation, material, dimension etc			Article No./Reference	
Designed by CompBlades	Checked by CompBlades	Approved by - date CompBlades - 20/09/13	File name	Date 20/09/13	Scale 1:20	
CompBlades.com			Blade Chassis - Lamination plan - Layers 4/5/6			
			METU_B_C_layers_040506	Edition 0	Sheet 1/1	