





| RevNo | Revision note | Date | Signature | Checked |
|-------|---------------|------|-----------|---------|
|-------|---------------|------|-----------|---------|



13.Triaxial (0/±45) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m²
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface le area = 0,0198m², Surface te area = 0,0194m²



14.Triaxial (0/+45) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m²
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface area = 0,4284m²



15. Triaxial (0/±45) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m²
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface le area = 0,0713m², Surface te area = 0,0649m²

The pictures show the blade in flattened state
Fabrication method : Wet hand Lay-up
Mean Wf (fiber weight fraction) = 0.55

| | | | | | | |
|---------------------------|----------|--|---|---|-----------------------|---------------|
| Itemref | Quantity | Title/Name, designation, material, dimension etc | | | Article No./Reference | |
| Designed by CompBlades | | Checked by CompBlades | Approved by - date CompBlades - 20/09/13 | File name | Date 20/09/13 | Scale 1:20 |
| CompBlades.com | | | | Blade Chassis - Lamination plan - Layers 13/14/15 | | |
| | | | | METU_B_C_layers_131415 | | Edition 0 |