





RevNo	Revision note	Date	Signature	Checked
-------	---------------	------	-----------	---------



10.Unidirectional E-Glass fabric: METYX L600E10C-0 of 623g/m²
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface area = 0,79 m²



11.Triaxial ($\pm 45/0$) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m²
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface area = 0,2398m²



12.Metallic Root Frame See drawing METU_B_AS_04

The pictures show the blade in flattened state
Fabrication method : Wet hand Lay-up
Mean Wf (fiber weight fraction) = 0.55

Itemref	Quantity	Title/Name, designation, material, dimension etc			Article No./Reference	
Designed by CompBlades	Checked by CompBlades	Approved by - date CompBlades - 20/09/13	File name	Date 20/09/13	Scale 1:20	
CompBlades.com				Blade - Suction side - Lamination plan - Layers 10/11/12		
				METU_B_S_layers_101112	Edition 0	Sheet 1/1