





RevNo	Revision note	Date	Signature	Checked
-------	---------------	------	-----------	---------



16.Triaxial ( $\pm 45/0$ ) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m<sup>2</sup>  
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403  
Surface le area = 0,05m<sup>2</sup>, Surface te area = 0,1049m<sup>2</sup>




17.Unidirectional E-Glass fabric: METYX L600E10C-0 of 623g/m<sup>2</sup>  
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403  
Surface area = 0,79 m<sup>2</sup>



18.Triaxial ( $\pm 45/0$ ) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m<sup>2</sup>  
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403  
Surface le area = 0,05m<sup>2</sup>, Surface te area = 0,1049m<sup>2</sup>

The pictures show the blade in flattened state  
Fabrication method : Wet hand Lay-up  
Mean Wf (fiber weight fraction) = 0.55

Itemref	Quantity	Title/Name, designation, material, dimension etc			Article No./Reference	
Designed by CompBlades	Checked by CompBlades	Approved by - date CompBlades - 20/09/13	File name	Date 20/09/13	Scale 1:20	
			Blade - Suction side - Lamination plan - Layers 16/17/18			
			METU_B_S_layers_161718		Edition 0	Sheet 1/1