





RevNo	Revision note	Date	Signature	Checked
-------	---------------	------	-----------	---------



Triaxial ($\pm 45/0$) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m²
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface area = 0,366m²



20.Foam thickness 10mm (0,7-2m): DIAB Divinycell H45
Foam thickness 5mm (2-3m): DIAB Divinycell H45
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface area = 0,6287m²



21.Triaxial ($0/\pm 45$) E-Glass fabric: METYX XL800E10F-0/45 of 835g/m²
Epoxy Resin: HUNSTMAN Araldite LY 3505/Hardener XB 3403
Surface area = 2,2506m²

The pictures show the blade in flattened state
Fabrication method : Wet hand Lay-up
Mean Wf (fiber weight fraction) = 0.55

Itemref	Quantity	Title/Name, designation, material, dimension etc		Article No./Reference	
Designed by CompBlades	Checked by CompBlades	Approved by - date CompBlades - 20/09/13	File name	Date 20/09/13	Scale 1:20
Blade - Suction side - Lamination plan - Layers 19/20/21				METU_B_S_layers_192021	Edition 0
					Sheet 1/1