

A Multi-Parametric Composite Approach for the Optimization of Wind Turbine Blades using Double-Double Laminates

Edgar Werthen¹, Gustavo Nunes Ribeiro¹, Sascha Dähne¹, Lennart Tönjes¹, David Zerbst¹, and Christian Hühne¹

¹DLR German Aerospace Center, Institute of Lightweight Systems, Lilienthalplatz 7, 38108 Braunschweig, Germany

Correspondence: Edgar Werthen (edgar.werthen@dlr.de)

Abstract. As wind turbines scale to meet growing energy demands, blade structures face increasingly demanding performance requirements. This work addresses this challenge by extending the design space of composite blades through the substitution of traditional triaxial laminates with ~~Double-Double (DD)~~ Double-Double (DD) laminates. While triaxial laminates are widely used due to their convenient layup and manufacturability, they are rarely scrutinized in literature and often lead to suboptimal structural performance. To enable this substitution, a multi-parametric composite modeling approach is developed and integrated into a gradient-based optimization framework. This architecture enables the coexistence of discrete and continuous laminate formulations within a single panel, allowing for detailed, skin-wise optimization of sandwich structures. The approach is applied to a modified blade design of the IEA-15-240 Reference Wind Turbine. Results demonstrate that DD laminates provide a more effective ~~buckling-oriented~~ design, resulting in significant mass savings in the shell structure.

1 Introduction

As wind turbines evolve to support greater energy supply, scaling rotor size has become essential to maximizing power output. The ~~annual-energy-production (AEP)~~ Annual Energy Production (AEP) increases proportionally to the square of the blade radius (Gasch and Twele, 2012), whereas blade mass scales to the power of around 2.4 with the blade radius (Rosemeier and Krimmer, 2022). This imbalance creates a structural challenge: increasing blade length raises the aerodynamic potential, but also increases mass and loads.

Composite materials have been fundamental in counteracting these trends. Beyond a high strength-to-weight ratio, their mechanical response can be tailored to the dominant load paths through ply orientation and stacking sequence. Unlike isotropic metallic alloys, fiber-reinforced laminates enable control of directional stiffness and coupling, improving structural efficiency. As a result, modern blades rely predominantly on composites, which account for approximately 93% of their structural weight (Liu and Barlow, 2017).

Although reinforced plastics offer significant potential for weight reduction, they also introduce challenges in design, analysis, optimization, and manufacture. Beyond selecting the fiber composition and matrix material, the layup configuration must be defined, including ply angles, stacking order, and thickness distributions.

In practice, blades are often designed using ~~generic laminate families with pre-established angles and thicknesses~~ predefined laminate families, which are then treated as homogenized transversely isotropic single layers for design and analysis. ~~Their widespread adoption~~ Following this practice, the blade designs of the International Energy Agency (IEA) Reference Wind Turbines (RWTs) make use of a set of laminates with pre-established angles and thicknesses (fabrics). This is also motivated by manufacturability, because more complex layups significantly increase cost, defect sensitivity, and tapering effort. Standardized families, particularly when produced with fabrics, reduce variability and simplify both production and structural modeling.

Aligned with industry trends and the demand for a new baseline in the 10–20 MW range, the IEA-IEA Wind TCP Task 37 introduced the IEA-IEA 15 MW RWT RWT in March 2020—an offshore turbine intended to push the state of the art (Gaertner et al., 2020). To accommodate higher power capture, the blade length and mass were scaled to 117 m and 65 t, respectively. Structurally, the design follows a traditional layout with two main spars and spar caps, complemented by shear webs that extend from 10% to 95% of the blade span. The triaxial glass laminate covers most of the structure, while the shear webs are reinforced with biaxial glass fibers. The internal volume, apart from key load-bearing components, is filled with medium-density foam in a sandwich configuration to limit weight. The trailing and leading edges feature a uniaxial glass laminate, while the spar caps employ uniaxial carbon laminate as the core material. The structural concept is shown in Figure 1.




Figure 1. IEA-IEA 15 MW structural concept. Source: (Werthen et al., 2023).

Beyond the specific architecture of the IEA-IEA 15 MW, the selection of laminate materials reflects a consistent trend across successive reference models—dominated by triaxial laminate applications. Early designs, such as the NREL 1.5 MW, 3 MW, and 5 MW reference wind turbines (Rinker and Dykes, 2018), extensively employed triaxial glass laminates, wrapping both the shell and spar webs. More recent baselines, including the DTU 10 MW (Bak et al., 2013), IEA-IEA 10 MW (Bortolotti et al., 2019), IEA-IEA 15 MW (Gaertner et al., 2020), and IEA-IEA 22 MW (Zahle et al., 2024), retain triaxial laminates primarily on the shell, while the spar webs employ biaxial laminates. Despite this evolution, triaxial materials still represent a substantial share of the overall blade mass.

A typical triaxial layup follows the sequence $[-45^\circ / 0^\circ / +45^\circ]$, comprising roughly 50% unidirectional (0°) and 50% off-axis ($\pm 45^\circ$) plies (Camarena et al., 2022). This configuration is attractive for its balanced response under general loading,

providing in-plane shear resistance, bending stiffness, and improved buckling performance (Castro, 2018). However, its near-generic character limits the tailoring of stiffness and directional coupling. For this reason, triaxial laminates are often adopted in less optimized industrial contexts due to their simplicity and generality (Samborsky and Mandell, 1996).

50 Building on the reference models, several studies explored blade optimization under different design settings. Sjølund and Lund (2018) optimized only the thickness of a variety of layers on a 73.5 m blade and achieved a 19.4% mass reduction. Serafeim et al. (2022) tailored spar-cap stiffness by rotating the UD fibers, obtaining a 5.8° off-axis solution and an 8.3% reduction on the DTU 10 MW blade. Hayat et al. (2022) conducted material and thickness optimization of the spar caps (glass, hybrid, carbon), reporting a reduction of up to 26.4%, consistent with the spanwise strategy adopted in the ~~IEA-IEA~~ 15 MW baseline. Scott et al. (2022) optimized the ~~IEA-IEA~~ 15 MW using thickness laws, material mix, and spar-cap position; however, under frozen loads, they required a 34.7% mass increase to recover stability. Extending stiffness tailoring, Couto et al. (2023) used region-wise laminate optimization with discrete angle sets but remained constrained by the limited orientations.

The vast, discrete design space of composite laminates intrinsically motivates simplifications in their description and design. Most commonly, ply orientations are fixed, and only thickness is scaled (e.g., (Sjølund and Lund, 2018; Hayat et al., 2022; 60 Scott et al., 2022)); in other cases, the space is restricted to a small discrete set of angles, reducing tailoring margin (e.g., (Couto et al., 2023)). A similar pattern appears in aeronautics, where quad-laminates—an extension of triax with an added 90° ply—are widely used; they deliver behavior closer to metallic alloys but at the cost of a more complex design and optimization pipeline (Tsai, 2021).

To address these limitations, Tsai (2021) introduced the ~~Double-Double-DD~~ Double-Double laminate class. A ~~DD-DD~~ 65 is defined by two angles (Φ, Ψ) forming the four-ply building block $[\pm\Phi, \pm\Psi]_r$ repeated r times. This yields a continuous, balanced parameterization with straightforward homogenization, making design and optimization less complex. A key advantage is tapering: building blocks can be dropped to transition between neighboring panels without symmetry constraints (~~Kappel et al., 2024~~), a common practice in the blade industry, thereby not introducing any complexity to the current standpoint. From a manufacturing standpoint, Kappel and Tsai (2024) demonstrated ~~DD laminates using prepreg~~ DD laminates using prepreps and vacuum infusion, predominantly prepreg-prepreps with off-the-shelf materials, which ~~is consistent with processes also used in~~ can be transferred to wind turbine blade production (~~Mishnaevsky et al., 2017~~) with new types of fabrics.

Almeida et al. (2025) surveyed the use of ~~Double-Double-DD~~ laminates across applications and discussed their implications. Notably, Garofano et al. (2023) compared ~~DD-DD~~ laminates with conventional layouts in fuselage structures and reported a 34% weight reduction. ~~Given the structural parallels between wings and blades—slender, tapered panels under complex loading,~~ 75 ~~Kappel (2022) applied DD laminates to aircraft wing panels and demonstrated about 8% weight savings relative to an already optimized metallic panel. Moreover,~~ Riccio et al. (2024) conducted this comparison for composite aeronautical components and reported mass savings of up to 50%. Zerbst et al. (2025) integrated a ~~Double-Double-DD~~ plate formulation into a gradient-based optimization environment for composite structures called *lightworks* (Dähne et al., 2024) and validated it on a wing-box case. These results highlight the weight-saving potential of ~~Double-Double-DD~~ laminates across aerospace structures and their 80 initial integration into *lightworks*.

Extending this capability to wind-turbine blades requires higher modeling fidelity, as blade panels are typically sandwich structures composed of multiple materials through the thickness. In practice, outer face sheets may follow a continuous ~~Double-Double-DD~~ description, whereas cores remain discrete laminates. Representing such combinations requires a clear parameterization strategy, in which each constituent material defines its own design variables, while consistently contributing to the overall panel response. To support this requirement, a modular and multi-parametric plate formulation is introduced. It allows for the independent parameterization of sub-components and their integration into a unified structural layer. This approach accommodates both continuous and discrete laminates within the same stack ~~, and enables the replacement of and enables replacing~~ conventional triaxial skins with ~~Double-Double-DD~~ laminates. This way, expanding the design space towards more adaptable stiffness behavior.

1.1 Objectives

In light of the above, the central objective of this study is to ~~enable~~ enlarge the design space for sandwich composite panels in the context of structural mass optimization ~~in-for~~ large wind turbine blades ~~by expanding the design space of sandwich composite panels~~. This is achieved by introducing ~~Double-Double-DD~~ laminates in place of the predefined stiffness-fixed triaxial laminates.

To make this substitution viable within sandwich panels, a multi-parametric composite approach is introduced and implemented in the *lightworks* optimization environment. The approach models sandwich structures as modular assemblies of independently parameterized sub-composites, enabling materials with different structural foundations, such as layer-based and continuous formulations, to coexist across the panel thickness.

This work naturally follows as a continuation of the study by Werthen et al. (2023), who employed *lightworks* for large-scale blade optimization using a simplified sandwich representation, in which each component (e.g., a triaxial laminate) was modeled as a single equivalent layer in the stack. In contrast, the present approach expands the formulation to incorporate ~~Double-Double-DD~~ laminates, which is demonstrated on the CRC-15-240 blade, an in-house modified version of the IEA-15-240 reference wind turbine. This constitutes the first application of ~~Double-Double-DD~~ laminates in wind turbine blade design and represents a step forward in advancing composite optimization for the wind industry.

1.2 Structure of the paper

The development of this work is organized into three consecutive phases, each addressing a distinct layer of the proposed methodology. All implementations are subjected to verification and testing, with feedback loops guiding refinements at each stage.

The first phase focuses on ~~Double-Double-DD~~ laminates as replacements for the triax. It includes reviewing the mechanical role and limitations of triaxial laminates, characterizing the stiffness and failure behavior of ~~Double-Double-DD~~ configurations, performing parametric load studies, and implementing a restricted “hard” variant with fixed $\Phi = 0^\circ$ for intermediate optimization tests.

The second phase extends the *lightworks* structural model to support multi-parametric composites. This involves developing a class to handle modular stacking, implementing algorithms for stiffness assembly and load distribution through the thickness, and integrating the formulation into the structural and optimization pipeline.

The third phase applies the methodology to the CRC-15-240 blade, demonstrating the practical use of the multi-parametric framework and ~~Double-Double-DD~~ laminates in large-scale optimization. This involves adapting auxiliary tools to the framework and analyzing outcomes in terms of mass reduction, design-space expansion, and material property distribution along the span.

The subsequent sections of this study are organized as follows. Section 2 investigates ~~Double-Double-DD~~ laminates in comparison to triaxial laminates. Section 3 introduces the multi-parametric approach and demonstrates it through a single-panel case. Section 4 applies the methodology to the CRC-15-240 blade, detailing the optimization setup. Section 5 presents a comparative assessment of results. Finally, Section 6 summarizes the key findings.

2 Characterization of ~~Double-Double-DD~~ and Triaxial Laminates

The ~~Double-Double-DD~~ laminate concept, introduced by Tsai (2021), represents a significant advancement in the efficient design of composite structures. Based entirely on the ~~Classical Laminate Theory (CLT)~~ Classical Laminate Theory (CLT), its formulation requires no additional assumptions and, notably, removes the need for mid-plane symmetry, traditionally imposed to avoid bending-extension coupling, simplifying design and manufacturing constraints.

A typical ~~DD-DD~~ laminate is composed of repeated ~~building blocks (BBs)~~ Building Blocks (BBs), each containing four plies arranged in two balanced angle pairs of Φ and Ψ . Among the possible stacking options, the configuration $[\Phi / -\Psi / -\Phi / \Psi]$ has been shown to yield superior homogenization characteristics (Tsai, 2021), and is therefore adopted throughout this work. The complete laminate is formed by repeating this block ~~r~~ r times through the thickness, resulting in the configuration $[\pm\Psi / \pm\Phi]_{rT}$, where the subscript ~~T~~ T denotes the total stack, following the Nettles convention (Nettles, 1994).

2.1 Homogenization

The main advantage of DD laminates lies in their potential for homogenization: as the number of building blocks increases, the bending and extensional stiffness matrices (~~$[D]$ and $[A]$~~ $[D]$ and $[A]$) approach proportionality, while the coupling matrix ($[B]$) tends toward zero. The resulting structure exhibits a layer-position-independent response with minimal coupling between in-plane and out-of-plane behaviors.

As reported in Zerbst et al. (2025), the normalized matrices exhibit characteristic dependencies on r . These trends indicate that with increasing r , the off-diagonal terms of ~~$[B^*]$~~ $[B^*]$ decay as $1/r$, while specific coupling terms in $[D^*]$ vanish at a rate of $1/r^2$. To formalize this, Tsai (2021) elaborated two conditions to be met for assumed homogenization:

$$\forall i, j \in \{1, 2, 6\} : \quad |A_{ij}^* - D_{ij}^*|, |B_{ij}^*| < \alpha \cdot \text{TSAI} \quad (1)$$

where α is a prescribed fraction of the Tsai modulus, defined as the trace of the ply stiffness matrix ($\text{TSAI} = \text{Tr}[\mathbf{Q}][\mathbf{Q}]$) ($\text{TSAI} = \text{Tr}[\mathbf{Q}]$). Acting as a threshold to define acceptable levels of coupling and stiffness mismatch, Tsai (2021) recommends

145 $\alpha = 0.02$.

Once these conditions are met, the laminate behavior can be approximated using only the extensional stiffness matrix $[\mathbf{A}]$, and the bending stiffness $[\mathbf{D}]$ can be derived as:

$$[\mathbf{A}] = \sum_{k=1}^4 \left([\bar{\mathbf{Q}}]_k \frac{t_{\text{lam}}}{4} \right), \quad [\mathbf{B}] = \mathbf{0}, \quad [\mathbf{D}] = \frac{t_{\text{lam}}^2}{12} [\mathbf{A}], \quad (2)$$

where $[\bar{\mathbf{Q}}]_k$ denotes the transformed reduced stiffness matrix of the k -th ply in the building block, dependent on $\pm\Phi$ or $\pm\Psi$.

150 Figure 2 shows that Tsai's homogenization criterion is satisfied for both the Triax and two DD laminates at four repetitions r . Since a DD laminate is defined by two angle pairs $[\pm\Psi/\pm\Phi]$, a Triax fabric can be interpreted as a DD laminate with $[0/0/-45/+45]$ as a single repetition r . The criterion depends solely on the number of repetitions, not on individual ply thickness, as the $[\mathbf{ABD}^*]$ matrices are normalized by the laminate thickness t_{lam} .




Figure 2. Homogenization criterion values for Triax and two DD laminates as a function of repetition count r .

2.2 Design Space

155 According to Tsai and Melo (2015a), any laminate can be described through lamination parameters: a continuous stiffness representation grounded in invariant theory. To characterize the design space of ~~Double-Double~~ DD laminates relative to conventional triaxial configurations, their formulation is briefly recalled.

The general formulation of the lamination parameters (V_x^A, V_x^B, V_x^D) can be expressed as follows, in accordance with Zerbst et al. (2025):

$$160 \quad V_x^A = \frac{1}{t_{\text{lam}}} \sum_{k=1}^N (z_k - z_{k-1}) W_x, \quad (3)$$

$$V_x^B = \frac{1}{t_{\text{lam}}^2} \sum_{k=1}^N (z_k^2 - z_{k-1}^2) W_x, \quad (4)$$

$$V_x^D = \frac{4}{t_{\text{lam}}^3} \sum_{k=1}^N (z_k^3 - z_{k-1}^3) W_x, \quad (5)$$

where $z_k - z_{k-1}$ is the distance from the k -th ply to the laminate mid-plane, and W_x are trigonometric functions of the ply angle θ_k :

$$165 \quad W_x = \begin{cases} \cos(2\theta_k), & x = 1, \\ \sin(2\theta_k), & x = 2, \\ \cos(4\theta_k), & x = 3, \\ \sin(4\theta_k), & x = 4. \end{cases} \quad (6)$$

For a homogenized DD-DD laminate, this formulation simplifies considerably. All coupling-related lamination parameters $V_{1,2,3,4}^B$ vanish, and due to the proportional nature of $[\mathbf{A}]$ and $[\mathbf{D}]$, the bending parameters equal the extensional ones ($V_x^A = V_x^D$). The resulting formulation thus reduces to four unique values, among which only V_1^A and V_2^A (and their bending counterparts) vary with the fiber angles Φ and Ψ :

$$170 \quad V_1^A = \frac{1}{2} [\cos(2\Phi) + \cos(2\Psi)] = V_1^D, \quad (7)$$

$$V_2^A = \frac{1}{2} [\cos(4\Phi) + \cos(4\Psi)] = V_2^D, \quad (8)$$

$$V_3^A = 0 = V_3^D, \quad V_4^A = 0 = V_4^D, \quad V_{1,2,3,4}^B = 0. \quad (9)$$

Thus, the entire design space of a DD-DD laminate can be visualized in the V_1^A - V_2^A plane, where each admissible combination of the angle pair $\{\Phi, \Psi\}$ maps to a specific point. Figure 3 illustrates the full DD-DD design space, as mathematically described in Zhao et al. (2023).

An important aspect to highlight is the role of the lamination parameter V_2^A . Laminates with $V_2^A \geq 0$ are classified as hard laminates due to their greater resistance to normal stresses, whereas those with $V_2^A < 0$ are called soft laminates, exhibiting improved shear and buckling performance.

A typical triaxial laminate can be interpreted as a particular case of the Double-Double-DD configuration, though with a stacking arrangement $[\pm 0 / \pm 45]$ that is not optimal for homogenization (Tsai, 2021). Owing to its position along the vertical axis of the design space, the triaxial laminate lies within the hard region. Nevertheless, the inclusion of $\pm 45^\circ$ plies determines a hybrid character, improving its shear and buckling resistance. Despite their practicality, triaxial laminates are ill-suited to




Figure 3. Design space of ~~DD~~DD laminates in the V_1^A – V_2^A plane.

optimization: they are fixed at a single point in the lamination-parameter space, enforcing a predefined normal–shear compromise. As a result, their capacity to adapt to specific load cases is limited, unless the optimal solution coincidentally aligns with
185 the same fiber orientations.

2.3 Strength Criterion

For discrete laminates, strength evaluations are typically performed at the ply level (i.e., Tsai-wu criterion). However, when employing a continuous homogenized formulation, ply-level evaluation becomes inconsistent with the design representation. In this context, a laminate-level failure criterion is essential to maintain continuous formulation without layup reconstruction.

190 One laminate-level alternative is the strain-based omni-envelope criterion proposed by Tsai and Melo (2015b). This method is derived from the classical quadratic failure criterion in stress space and reformulated in strain space. The general form of the failure condition is expressed as:

$$H_{ij}\varepsilon_i\varepsilon_j + H_i\varepsilon_i = 1 \quad (10)$$

where H_{ij} and H_i are material-dependent coefficients derived from strain invariants. These coefficients depend on the stiffness
195 matrix and ply orientation, and their derivation is detailed in Kappel (2023).

The omni-envelope extends the ply-level criterion by superimposing the strain-space envelopes of unidirectional plies across all fiber orientations present in the laminate, following the Tsai-wu criterion (Kappel, 2022). The result is a global strain envelope that represents the union of all individual failure surfaces. Zerbst et al. (2025) discusses its use for ~~double-double~~DD laminates using *lightworks*.

200 **2.4 Design Space Exploration under In-Plane Loads**

Under distinct loading conditions, ~~double-double-DD~~ laminates adjust their angles to optimize the response in relation to a specific objective (e.g. τ -mass), exploring the full design space capacity previously shown in Figure 3. This analysis considers only strength constraints, provided by the omni-envelope criterion, and disregards any stability assessment. The focus remains exclusively on material-level response.

205 The exploration includes pure and combined loading conditions involving uniaxial (n_x) and shear loads (n_{xy}): a scenario similar to the wind turbine blade application explored in this study. The load cases are summarized in Table 1.

Table 1. In-plane load combinations used for design space exploration.

Case #	Name	n_x [N m ⁻¹]	n_{xy} [N m ⁻¹]
1	UD -UD Tension	$+1.0 \times 10^6$	0
2	UD Compression	-1.0×10^6	0
3	Pure Shear	0	2.0×10^5
4	Tension + Shear	$+1.0 \times 10^6$	5.0×10^5
5	Compression + Shear	-1.0×10^6	5.0×10^5

Under axial tension and compression (Cases #1 and #2), the optimized ~~DD-DD~~ laminate aligns both fiber angles with the load direction, defined here as $\Phi = \Psi = 0^\circ$, since the fibers act as the primary load carriers. Figure 4 illustrates the resulting mass distribution across different angle combinations: while the ~~DD-DD~~ laminate converges to the optimal alignment, the triaxial configuration remains fixed, with one angle aligned with the load and the other offset by 45° , resulting in a mass increase. The compressive case exhibits nearly identical behavior, differing only in allowable limits due to the material’s higher tensile strength.

215 When subjected to pure shear (Case #3), the optimal stacking shifts toward intermediate angles, with 45° emerging as the dominant orientation, as shown in Figure 5. This response reflects classical shear mechanics, where maximum shear stress (τ_{12}) is resolved along $\theta = 45^\circ$ planes, producing a corner-driven deformation mode that is best resisted by fibers oriented in those directions. Once more, the triax shows mass increase due to additional non-optimized 0° plies.

In the tension–shear case (Case 4#), shown in Figure 6, the optimal fiber angles shift toward lower values, corresponding to the hard-laminate region. The solution remains offset from the $(0,0)$ coordinate, with both Φ and Ψ lying between 0° and 45° . This trend is consistent with the pure tension and pure shear responses previously observed in Figure 4 and Figure 5.

220 Conversely, the compression–shear interaction (Case 5#), illustrated in Figure 7, produces a markedly different result. The optimized angles shift toward higher values, which increases the off-axis orientation and, as a consequence, generates larger transverse normal stress $\sigma_2\sigma_2$.

This behavior follows directly from the Tsai–Wu interaction terms, shown in Figure 8: the shear strength is coupled with the transverse normal stress, such that moderate compression in the 2-direction increases the effective shear strength. Physically,




Figure 4. Optimized mass distribution for the DD laminate under axial tension.




Figure 5. Optimized mass distribution for the ~~DD~~-DD laminate under pure shear loading.

225 this corresponds to the fibers being laterally constrained by the matrix, which delays shear-driven failure. However, once σ_2 becomes sufficiently large, the quadratic compression term dominates, and the allowable shear strength drops again. This mechanism explains why the proportion n_x/n_{xy} is critical for determining the optimal angle shift in this case.

These results underscore that stiffness-based tailoring, even in its simplified form, captures design freedoms that are unexplored by triaxial laminates, whose fixed fiber arrangement constrains their ability to adapt to varying loads.




Figure 6. Optimized mass distribution for the $\overline{DD}$ - $\overline{DD}$ laminate under combined tension and shear loading.




Figure 7. Optimized mass distribution for the $\overline{DD}$ - $\overline{DD}$ laminate under combined compression and shear loading.

230 3 Multi-Parametric Composites

Conventional structural models in structural optimization, such as those used in previous large-blade studies, describe each panel through a set of homogenized layers (e.g. Sjølund and Lund (2018); Hayat et al. (2022); Scott et al. (2022); Werthen et al. (2023)). While efficient, this approach simplifies the internal composition of sandwich structures into equivalent layers within a laminate, typically limited to three homogenized materials.

235 The multi-parametric formulation introduces a modular description of composite panels (Figure 9). Each panel is decomposed into a stack of independently parameterized sub-composites, each retaining its own material model and design variables. This structure allows, for example, Double–Double laminates to coexist with unidirectional or foam components within the




Figure 8. Tsai-Wu τ_{12} - σ_2 failure envelope. Source: Daniel et al. (2011).

same stack. Design variables are defined at the composite level, enabling independent control of each sub-component's parameters, such as fiber angles and thickness, without constraining them to a single, homogenized behavior. Whereas conventional models assemble stiffness from individual laminate layers, the new approach computes and ~~superposes~~ superimposes the stiffness of each composite sub-component, maintaining analytical consistency while expanding the design space available for optimization.

3.1 Stiffness Superposition

To enable a generalized treatment of stiffness for any combination of composite formulations, the stack must be interpreted as a sequence of materials, each characterized solely by its stiffness matrix, thickness, and position across the panel's thickness. This abstraction enables the creation of a global stiffness matrix $[\mathbf{ABD}]_{\text{global}}$ from various combinations of materials, regardless of whether the underlying model is discrete or continuous. As long as each material supplies its individual stiffness matrix $[\mathbf{ABD}]_{\text{local}}$ and total thickness, the modular integration remains intact.

The core principle enabling stiffness superposition is the analytical shift of the reference plane for each component, from its original mid-plane, as defined in Classical Laminate Theory, to a common reference shared across all material blocks. This alignment allows for the consistent transformation of stiffness contributions, enabling their direct summation into a global stiffness matrix. The entire process is fully grounded in the CLT without introducing any additional assumptions.

Figure 10 illustrates the concept of an arbitrary reference plane shift for a single laminate.

For such a shift, the position of any point along the thickness can be expressed as:

$$z^{new} = z^0 + \Delta z, \quad (11)$$




Figure 9. Conceptual comparison between the discrete-homogenized and multi-parametric formulations.




Figure 10. Plane shift from the original mid-plane.

where z^0 is the coordinate with respect to the original reference plane, Δz is the signed offset between the planes, and z^{new} is the transformed coordinate relative to the new reference.

Using this definition, the transformed stiffness matrices $[\mathbf{A}^{new}]$, $[\mathbf{B}^{new}]$, and $[\mathbf{D}^{new}]$ can be defined as:

$$[\mathbf{A}^{new}] = \sum_k [\bar{\mathbf{Q}}_k] [z_{k-1}^{new} - z_k^{new}], \quad (12)$$

260

$$[\mathbf{B}^{new}] = -\frac{1}{2} \sum_k [\bar{\mathbf{Q}}_k] \left[(z_{k-1}^{new})^2 - (z_k^{new})^2 \right], \quad (13)$$

$$[\mathbf{D}^{new}] = \frac{1}{3} \sum_k [\bar{\mathbf{Q}}_k] \left[(z_{k-1}^{new})^3 - (z_k^{new})^3 \right]. \quad (14)$$

By substituting Equation 11 into Equations 12, 13 and 14, and expanding each term, the transformed stiffness matrices can be written as functions of the original matrices (0) and the shift Δz . The resulting transformations are shown below, while their derivations are provided in Appendix A:

$$\begin{aligned} [\mathbf{A}^{new}] &= [\mathbf{A}^0], \\ [\mathbf{B}^{new}] &= [\mathbf{B}^0] + \Delta z [\mathbf{A}^0], \\ [\mathbf{D}^{new}] &= [\mathbf{D}^0] + 2\Delta z [\mathbf{B}^0] + \Delta z^2 [\mathbf{A}^0]. \end{aligned}$$

(15)

Once the $[\mathbf{ABD}]$ formulation is derived with respect to an arbitrary reference plane, the superposition of multiple composites can be consistently established. Figure 11 illustrates a generic stack composed of multiple material blocks, each contributing to the overall stiffness, given the plane shift to a common one.




Figure 11. Superposition of different composite blocks.

Although the reference plane could, in theory, be positioned arbitrarily. In general, the mould (and aerodynamic) surface should be used as the reference plane along the z -axis, it is imposed to avoid overestimation of the bending stiffness. In the present study, the reference is set to coincide with the mid-plane of the whole stack. This aligns the computed stiffness terms, consistent with the plate formulation, where in which loads and deformations are defined relative to the mid-plane. The resulting superposition formulation is given in Equations 16, 17, and 18.

$$[\mathbf{A}] = \sum_k [\mathbf{A}_k^0] \quad (16)$$

$$[\mathbf{B}] = \sum_k ([\mathbf{B}_k^0] + \Delta z_k [\mathbf{A}_k^0]) \quad (17)$$

$$[\mathbf{D}] = \sum_k ([\mathbf{D}_k^0] + 2\Delta z_k [\mathbf{B}_k^0] + \Delta z_k^2 [\mathbf{A}_k^0]) \quad (18)$$

3.2 Load Distribution

In the context of structural assessment, stability and strength evaluations operate at distinct hierarchical levels. Stability is assessed at the panel level, based on the global geometry, stiffness matrix, and applied loads. Once the governing criterion is defined, the procedure follows a fixed analytical pipeline dependent solely on these macroscopic parameters. Strength evaluation, in contrast, is performed at the material level to capture the behavior of each constituent composite. This requires distributing the global load state across the individual components of the stack so that each sub-composite is assessed independently according to, based on its local strain field and failure criterion.

From the solver, each panel receives a set of membrane forces ($\mathbf{N}$) and bending moments ($\mathbf{M}$), which serve as the input loads for subsequent evaluations. For strength assessment, these loads are converted into strain quantities using the plate stiffness relation shown in, obtained through inversion of the $[\mathbf{ABD}]$ matrix. This operation yields the mid-plane strain ϵ^0 and curvature κ for the panel.

$$\begin{Bmatrix} \epsilon^0 \\ \kappa \end{Bmatrix} = \begin{bmatrix} [\mathbf{A}] & [\mathbf{B}] \\ [\mathbf{B}] & [\mathbf{D}] \end{bmatrix}^{-1} \begin{Bmatrix} \mathbf{N} \\ \mathbf{M} \end{Bmatrix}.$$

As defined in, the strain at any point through the thickness of a laminate is represented as a superposition of membrane strain and bending-induced curvature:

$$\begin{Bmatrix} \epsilon_x \\ \epsilon_y \\ \gamma_{xy} \end{Bmatrix} = \begin{Bmatrix} \epsilon_x^0 \\ \epsilon_y^0 \\ \gamma_{xy}^0 \end{Bmatrix} + z \begin{Bmatrix} \kappa_x \\ \kappa_y \\ \kappa_{xy} \end{Bmatrix}.$$

When curvature is non-zero, the resulting strain varies linearly through the laminate thickness for each strain component. This behavior is illustrated in [following the plate stiffness relation described in VDI \(2014\)](#). Resultant strain for a laminate under membrane and bending loads:

In a multi-composite stack, the same principle of linear strain distribution applies. However, to preserve the modularity of the multi-parametric composites formulation, each composite must be evaluated independently with respect to its position within the stack.

This is achieved by mapping the global deformation state, defined by the mid-plane strain and curvature of the entire laminate, into a local strain state for each individual skin. Specifically, a relative mid-plane strain is computed for each skin, accounting for the contribution of curvature based on the vertical offset between the global mid-plane and the mid-plane of the corresponding sub-skin.

Mathematically, the local mid-plane strain for each sub-skin is given by:-

$$\underline{\varepsilon_{\text{sub-skin}}^0 = \varepsilon_{\text{global}}^0 + \Delta z \cdot \kappa}$$

where Δz denotes the signed distance between the mid-plane of the sub-skin and the global mid-plane of the stack.

Consequently, the strain distribution within each sub-skin can be expressed as:-

$$\underline{\varepsilon_{\text{sub-skin}}(z) = \varepsilon_{\text{sub-skin}}^0 + \kappa \cdot z, \quad z \in \left[-\frac{t_{\text{sub-skin}}}{2}, \frac{t_{\text{sub-skin}}}{2} \right]}.$$

This piecewise formulation results in a segmented strain profile across the laminate thickness, with each segment corresponding to a distinct material block. Importantly, it ensures that each skin is evaluated using its own local reference and geometry, entirely decoupled from the global assembly. An example of this concept is illustrated in

Strain modularization concept

4 CRC-15-240 Blade Optimization

The blade analyzed in this study is based on the structural layout of the IEA-15-240 Reference Wind Turbine. This reference configuration features a blade span of approximately 117 meters and a total mass of 65 t. Structurally, the blade comprises two main spars, along with leading edge (LE) and trailing edge (TE) reinforcements, all extending from 10% to 95% of the span.

Internally, the structure combines triaxial glass fiber laminates in the outer shell with core materials that vary along span and circumference. UD Carbon laminates are used in the spar caps to provide high bending stiffness with minimal added mass, while UD Glass layers reinforce the leading and trailing edges under edgewise loading. Foam cores occupy the space between spar caps and edge reinforcements beyond the root, improving buckling resistance and bending stiffness. The shear webs are also built as sandwich panels, using biaxial glass face sheets bonded to foam. Figure 12 illustrates this composition at four representative cross-sections along the blade span.

The IEA-15-240 material dataset provides a solid reference basis but contains a few undefined parameters, including Poisson's ratios for biaxial and triaxial glass laminates, as well as some missing properties for the unidirectional carbon material.




Figure 12. Cross-section schematics for different spanwise locations in the CRC-15-240 blade.

325 To enable a comprehensive structural assessment, the CRC-15-240 blade utilizes the material definitions from the IEA-22-240 Reference Wind Turbine (Zahle et al., 2024), which provides an updated dataset developed by Camarena et al. (2022). For all laminates, the material coordinate system is defined such that the E_1 direction is oriented spanwise, tangential to the shell reference surface. The values used in this study are summarized in Table 2.

Moreover, panel-level analyses of the baseline model reveal localized instability near the blade tip, where spar caps taper and the leading and trailing edge reinforcements are discontinued, as reported by Scott et al. (2022). To mitigate this effect and increase bending stiffness in these regions, the CRC-15-240 model introduces foam cores where the reinforcements are absent, thereby maintaining a continuous sandwich configuration along the blade span.

The following sections describe the complete simulation and optimization framework employed for the CRC-15-240 blade. Simulation Setup details the aeroelastic analyses, load processing procedures, and the solver–optimizer integration environment. Structural Model Initialization introduces the spanwise and circumferential discretization of the blade. Loading and Boundary Conditions summarizes the design load cases and the procedure for extracting the load envelopes. Coupling and Constraints specifies the structural requirements imposed during the optimization process. Finally, Parametrization and Optimization Setup presents the parametrization strategies adopted in the analysis and provides an overview of the optimization workflow.

Table 2. Mechanical properties of composite and isotropic materials used in the CRC-15-240 blade. Composite values from Camarena et al. (2022).

Property	Uniaxial glass	Biaxial glass	Triaxial glass	Uniaxial carbon	Foam
E_1 [GPa]	43.70	11.02	28.21	157.6	0.1425
E_2 [GPa]	16.50	16.05 <u>11.02</u>	16.05 <u>16.24</u>	9.1	0.1425
E_3 [GPa]	15.45	16.05	15.45 <u>15.84</u>	9.1	0.1425
G_{12} [GPa]	3.495	3.488 <u>13.23</u>	3.495 <u>8.248</u>	4.131	–
G_{13} [GPa]	3.480	3.488	3.480 <u>3.491</u>	4.131	–
G_{23} [GPa]	3.480	3.488	3.480 <u>3.491</u>	3.488 <u>2.689</u>	–
ν_{12} [-]	0.35 <u>0.262</u>	0.345 <u>0.6881</u>	0.345 <u>0.4975</u>	0.30 <u>0.3133</u>	0.3194
ν_{13} [-]	0.35 <u>0.264</u>	0.345 <u>0.1172</u>	0.345 <u>0.1809</u>	0.30 <u>0.3133</u>	0.3194
ν_{23} [-]	0.264 <u>0.35</u>	0.172 <u>0.1172</u>	0.274 <u>0.2748</u>	0.407 <u>0.4707</u>	0.3194
X_t [MPa]	640.23	461.24 <u>46.21</u>	435.65 <u>435.63</u>	1215.0 <u>1285.0</u>	2.083
X_c [MPa]	–370.7	–70.69	–33.41 <u>343.1</u>	–878.2	1.563
Y_t [MPa]	196.10 <u>38.1</u>	186.4 <u>46.21</u>	180.0 <u>76.44</u>	92.1 <u>38.1</u>	2.083
Y_c [MPa]	–82.18	–70.69	–17.67 <u>174.7</u>	–38.2 <u>82.18</u>	1.563
S [MPa]	113.8 <u>30.17</u>	78.0 <u>124.5</u>	78.0 <u>85.06</u>	131.6 <u>30.17</u>	1.250
T <u>R</u> [MPa]	18.97	18.97	18.97	45.4 <u>18.97</u>	1.250
<u>T</u> [MPa]	<u>6.21</u>	<u>6.21</u>	<u>6.21</u>	<u>6.21</u>	<u>1.250</u>
ρ [kg/m ³]	1940	1940	1940	1600	130

340 4.1 Simulation Setup

The simulation and optimization of the CRC-15-240 blade are conducted using a modular pipeline that integrates aeroelastic simulation, load processing, structural modeling, and gradient-based optimization. The overall workflow is shown in Figure 13, illustrating the data exchange between the main tools involved.

At the core of this process lies the `lw4wind`¹ environment, which manages communication between all modules. The simulation begins with an aeroelastic analysis in OpenFAST, generating time series of aerodynamic and inertial loads along the blade span. These results are then embedded into a WindIO file (Bortolotti et al. (2022)), an ontology ~~sehema~~scheme that defines the storage of wind turbine engineering parameters in a hierarchical yaml structure.

After load embedding, the pipeline proceeds to the structural modeling stage. The WindIO file is parsed through the CPACS interface, which performs the format conversion and initializes the structural solver *PreDoCS*. This stage defines the spanwise structural representation of the blade and sets up the optimization problem.

¹Short for “*Lightworks* for Wind”




Figure 13. Simulation methodology.

PreDoCS (Preliminary Design of Composite Structures, (Werthen et al., 2024)) performs the structural analysis of the blade as a continuous anisotropic beam governed by Timoshenko theory. During initialization, the blade span is discretized into cross-sectional stations, for which section properties and fully coupled 7×7 stiffness matrices are assembled. The solver computes the spanwise displacement field under applied external loads, from which internal loads are recovered using the cross-sectional stiffness relations described by Jung and Nagaraj (2002).

Once initialized, *lightworks* takes over the local structural representation, mapping each beam section to a detailed set of composite panel models. During optimization, *PreDoCS* and *lightworks* operate in parallel: *PreDoCS* provides the individual panel load states, while *lightworks* evaluates local stiffness, strength, and stability responses. Following convergence, the optimization results are post-processed.

4.2 Structural Model Initialization

After conversion of the blade geometry to the CPACS format, the model is segmented into structural panels. Circumferentially, each cross-section is divided into regions following WindIO conventions, which define the structural layout illustrated in Figure 12 for different span positions.

In the spanwise direction, the blade is discretized using a two-zone uniform scheme. From the root (0–23% span), panels are spaced at 2.60 m to capture the highly loaded root region and the transition from the cylindrical base to the main blade with spars. Beyond 23% span, a coarser spacing of 4.50 m is applied up to the tip, reducing computational cost while maintaining geometric continuity and manufacturability, given that taper plays ~~in an~~ important role in composite panels design. The model comprises 30 cross-sections in total. Since internal loads are evaluated analytically, a finer discretization is not required. A maximum envelope criterion is applied for load selection, ensuring conservative results.

370 In addition to spatial control, the sections are aligned with the blade’s actual load axis, which follows the curved blade geometry. The resulting model is visualized in Figure 14.




Figure 14. Structural discretization of the CRC-15-240 blade in *PreDoCS*.

4.3 Loading and Boundary Conditions

The loads used in this analysis represent the transient response of the nominal IEA-15-240 reference model. Aero-servo-elastic simulations are performed in OpenFAST using the ElastoDyn module, which applies an Euler–Bernoulli beam formulation
 375 with two bending modes: flapwise and edgewise deflections (Rinker et al., 2020). Building upon the structural analysis of the scaled 22 MW blade presented by Werthen et al. (2023), a reduced subset of design load cases is defined in accordance with the guidelines of DNVGL-ST-0376 (DNV GL, 2015a). The selected load cases are summarized in Table 3.

Table 3. Design load cases and corresponding wind speeds used in the simulation.

DLC number	Description	Mean wind speeds (m/s)
DLC 1.5	Extreme wind shear (vertical, positive and negative horizontal wind shear)	10.6 (rated)
DLC 1.6	Power production, NTM	10, 13, 18, 21
DLC 6.1	Extreme wind, 50-year storm, yaw misalignment of $\pm 8^\circ$	50

For each load case, time series of aerodynamic and inertial loads are post-processed to extract the critical design conditions. Following the DNVGL-ST-0376 guideline (DNV GL, 2015a), envelopes of all force and moment components are generated
 380 by evaluating their minimum and maximum values, including additional bending moments computed in the flap–edgewise plane at 30° intervals from 0° to 180° . The corresponding time steps associated with the maximum flapwise and edgewise tip deflections are also included.

4.4 Coupling and Constraints

The model is subject to five categories of constraints: coupling, strength, stability, taper, and deflection. A safety factor of 1.5 is applied to all evaluated constraints, whereas coupling relations are enforced directly and therefore excluded from this factor, following the definitions adopted by Werthen et al. (2023).

Coupling relations are applied to ensure consistent material behavior across the blade. Intra-panel coupling enforces symmetry through the sandwich thickness, mirroring the outer composite about the mid-plane while maintaining the uniqueness of the core. Inter-panel coupling links corresponding composites between the upper and lower shells, ensuring material symmetry despite their geometric differences. These relations remain fixed throughout the optimization.

Strength constraints are applied at the composite level and depend on the specific class of each material. For those modeled as single-ply laminates, the Tsai-Wu criterion (Amabili, 2018) is employed. ~~For Double-Double (DD), widely used in structural analysis and optimization studies due to its computational efficiency and limited material parameter requirements.~~ For DD laminates, the Omni-Envelope criterion is adopted, as detailed in subsection 2.3. Finally, the foam cores, due to their isotropic behavior, are evaluated using the von Mises criterion.

Fatigue constraints are applied to the laminates as a simplified maximum strain criterion, based on strain limits considered sufficiently conservative for use without material testing (DNV GL, 2015b):

$$\frac{R_d}{\gamma_m} = 0.35\% \quad (\text{tensile}), \quad (19)$$

$$\frac{R_d}{\gamma_m} = 0.25\% \quad (\text{compression}) \quad (20)$$

where γ_m is the material safety factor and R_d is the design value of the material property. These limits are verified for all four ply orientations of the DD laminate at each optimization step.

Stability constraints are evaluated at the panel level to account for local buckling under axial compression and in-plane shear. Assuming an orthotropic and symmetric laminate, the critical buckling load per unit width under compression is given by (Structural Analysis Working Group I, 2009, HSB-45112-02) as:

$$N_{x,\text{cr}} = k_x \left(\frac{\pi}{b} \right)^2 \sqrt{\tilde{D}_{11} \tilde{D}_{22}}, \quad (21)$$

and, for shear-dominated buckling, by (Structural Analysis Working Group I, 2009, HSB-45111-08) as:

$$N_{xy,\text{cr}} = k_s \left(\frac{\pi}{b} \right)^2 \sqrt[4]{\underline{D} \tilde{D}_{11} \underline{D} \tilde{D}_{22}^3}. \quad (22)$$

Here, $\tilde{D}_{11}$, $\tilde{D}_{11}$ and $\tilde{D}_{22}$ denote the laminate's effective bending stiffness terms, while ~~k_x and k_s~~ k_x and k_s are the buckling coefficients for compression and shear, respectively. These coefficients are interpolated from the provided curves, assuming simply supported boundary conditions for all panel edges to yield conservative estimates.

To account for through-thickness shear effects in the buckling analysis of sandwich panels, both critical buckling loads (compression and shear) are modified following (Kassapoglou, 2013):

$$N_{x/xy,cr,new} = \frac{N_{x/xy,cr}}{1 + \frac{k N_{x/xy,cr}}{t_c G_c}}, \quad (23)$$

where t_c and G_c denote the core thickness and transverse shear modulus, respectively, and k is the shear correction factor, set to $k \approx 1$. This choice is conservative for sandwich panels, where the core shear stiffness is low relative to that of the face sheets (Kassapoglou, 2013).

Since both axial and shear loads act simultaneously, the overall stability assessment combines the two modes through the interaction criterion proposed by (Peters, 1954):

$$R_x + R_s^2 \leq 1, \quad (24)$$

where R denotes the ratio between the applied and critical load for each mode.

Tapering constraints prevent abrupt thickness variations between adjacent panels. All materials satisfy the DNVGL-ST-0376 requirements (DNV GL, 2015a), except for the shell face sheets, which show a localized acute thickness drop near the root–mid-span transition where spars and reinforcements are introduced. Following Tsai (2021), a specific constraint is applied to the ~~Double-Double~~ DD laminates, allowing taper ratios up to 7.5:1.

Deflection constraints are added to all use cases to limit the maximum allowable blade tip displacement under extreme load cases. These constraints ensure the tower clearance of the blades.

4.5 Parametrization and Optimization Setup

Each panel in the blade is initialized with a multi-parametric scheme that enables multi-layer sandwich configurations composed of distinct sub-components, allowing each layer to be parametrized independently. Glass unidirectional, biaxial, and unidirectional carbon laminates are modeled as transversely isotropic single plies, while the foam core is treated as isotropic. These composites are optimized solely by their thicknesses across different panels.

The main innovation is the substitution of the triaxial glass laminates with Double–Double laminates, moving from a homogenized $[0_2/\pm 45]$ stacking to a configuration composed of unidirectional glass plies, which can be tailored in thickness and stiffness through the ply angles (Φ, Ψ) . To ensure consistent comparison, the baseline case also employs the ~~DD~~ DD formulation with fixed angles $[0/\pm 45]$, equivalent to the nominal triaxial stacking and part of the ~~DD~~ DD design space (Figure 3). This substitution removes inconsistencies in material properties and strength criteria, allowing all configurations to be assessed within a unified modeling approach.

Building upon this baseline, a series of simulation cases is defined with increasing levels of design freedom regarding the ~~Double-Double~~ skin parametrization. The different optimization scenarios are shown in Table 4.

In all cases except DD-Local, the fiber angles are uniform across all panels, meaning each panel adopts the same globally optimized orientation. Only the laminate thicknesses vary along the blade span. The locally optimized case is introduced to

Table 4. Comparison of ~~Double-Double-DD~~ laminate configurations and variable definitions.

Config.	Description	Number of variables	Remarks
Triax	DD-DD laminate with fixed 0° , 45° angles	1 thickness per section	Basis case, mimicking triax laminates
DD-Hard	DD laminate with fixed 0° , and Ψ variable	1 thickness per section and 1 global angle	DD with hard behavior restriction
DD	DD laminate with variable Φ and Ψ	1 thickness per section and 2 global angles	Classic DD
DD-Local	DD laminate with individualized set of angles per cross-section	1 thickness per section and 2 angles per section	Idealistic case, stiffness benchmark case

explore the potential of angle tailoring per cross section along the blade in response to localized structural demands. While not directly manufacturable, this configuration provides insights into the maximum achievable performance through local stiffness adaptation.

445 An overview of the materials employed in the CRC-15-240 blade and their corresponding parametrization strategies is presented in Table 5.

Table 5. Material models and parametrization strategies in the CRC-15-240 optimization.

Material	Region	Parametrized Properties	Remarks
UD Glass	LE/TE reinf. core	Thickness	Transversely Isotropic
UD Carbon	Spar cap	Thickness	Transversely Isotropic
Biaxial Glass	Web face sheet	Thickness	Transversely Isotropic
Foam	Web/Shell core	Thickness	Isotropic
Glass DD	Shell face sheet	Thickness, Φ , Ψ	Orthotropic

The optimization aims to minimize the total structural mass of the blade, subject to strength, simplified fatigue, stability, taper, deflection, and coupling constraints. The problem is solved using the Sparse Nonlinear OPTimizer (SNOPT), a gradient-based sequential quadratic programming algorithm that solves large-scale constrained problems through iterative quadratic approximations. Preliminary tests showed that SNOPT achieved more robust convergence than the Interior Point Optimizer (IPOPT) and the Method of Moving Asymptotes (MMA). The solver parameters follow standard definitions, except for the feasibility and optimality tolerances, which are set to 10^{-4} . For the usage of gradients, a check of the robustness of the results against varying initialization and perturbations has to be performed. Optimizations are started from different DD angle combinations like described in Zerbst et al. (2025). The mass optimum could be achieved with a reliability of over 90%. The overall optimization framework is summarized in Table 6.

450

455

Table 6. Optimization formulation scheme.

	Constraint/Variable	Description	Bounds
Minimize	m	Mass of ...	
On the basis of	n_x, n_y n_x, n_y	Panel loads (Axial forces, shear)	
With respect to	Φ in [deg]	First double double angle	[0, 90]
	Ψ in [deg]	Second double double angle	[0, 90]
Subject to	$g_{stability}$	Panel buckling	≤ 0
	$g_{strength}$	Strength Omni-FPF	≤ 0
	$g_{fatigue}$	Max. strain in fiber direction	≤ 0

5 Results

The optimization outcomes for all design cases are summarized in Table 7. The triaxial and DD-Hard configurations yield nearly identical masses ~~, differing by only 1.17% (839.8 kg). This~~ which indicates that the 0° plies dominate the overall stiffness, while the second angle exerts only a minor influence. In contrast, introducing full angular freedom in the DD case results in a mass reduction of ~~8.84% (6348.64% (2800 kg))~~ 8.84% (6348.64% (2800 kg)) relative to the triaxial baseline, highlighting the relevance of full directional control of the fiber orientations. The DD-Local case, which permits section-wise variation of Φ and Ψ , achieves ~~only a marginal~~ an additional improvement of 1.38% (~~901.51000 kg~~) compared to the DD case, ~~demonstrating that the globally optimized configuration already captures most of the achievable gains.~~

Table 7. Comparison of mass and optimized angles for each design case.

Parameter	Triax	DD-Hard	DD	DD-Local
Mass [t]	71.834 <u>75.5</u>	70.995 <u>75.35</u>	65.486 <u>72.7</u>	64.585 <u>71.7</u>
Φ [deg]	0	0	48 <u>37.0</u>	–
Ψ [deg]	45	49.2 <u>48.6</u>	48 <u>37.0</u>	–

~~Regarding the~~ The optimized fiber orientations ~~, the results indicate~~ show a general shift toward ~~laminates favoring buckling and shear resistance, typically characterized by plies around 45°~~ softer laminates in the direction of $\pm 45^\circ$, reflecting a compromise between spanwise stiffness and buckling resistance. This trend is illustrated in Figure 15, which ~~shows the stiffness of each configuration in~~ maps each configuration onto the lamination parameter design space.

The Triax configuration remains fixed, while the DD-Hard model slightly increases the second angle to reduce axial stiffness along the span. Despite this adjustment, both configurations exhibit similar stiffness behavior, positioned within the “hard” region identified by Tsai (2021). This explains the marginal difference in their optimized masses, as the limited variation of approximately ~~4.2–3.5°~~ in the second angle produces ~~minimal stiffness changes~~ only minimal changes in stiffness.




Figure 15. Case-related stiffness in LP design space

In contrast, the DD case, where both angles are freely optimized, is driven toward the **softest softer** region of the lamination parameter space, **centered around near the $\pm 45^\circ$ and near the lower** boundary of the feasible domain. This **outcome reflects a clear preference for shear and buckling-dominated behavior** reflects a structural preference for combining spanwise stiffness with shear and buckling resistance, with Φ and Ψ converging to approximately 48° . **A comparable pattern appears in the 37° .** The DD-Local case **where the section-wise optimized angles cluster within the same soft region, confirming the consistency of the global DD solution** follows a similar trend for most panels, though softer angles are adopted in the trailing edge panels of the rear shell to prevent local buckling, and 90° orientations appear near the maximum chord region (at 27 m), contributing edgewise bending stiffness in this region.

The spanwise mass distribution for all configurations is presented in Figure 16. The influence of laminate stiffness tailoring is evident: shell stiffness directly governs the structural mass profile. The Triax and DD-Hard cases exhibit nearly identical distributions **near the root, with a slight divergence emerging beyond mid-span due to the enhanced shear and buckling resistance of the DD-Hard laminates.**

Nevertheless, the total mass difference between the Triax and DD cases amounts to **6348.62800** kg. The root region, marked by a significant mass drop, accounts for approximately **6470%** of the total reduction (**4066.61960** kg), while the remaining **36% (228230% (840** kg) is distributed along the mid-span and tip. This concentration of mass reduction near the root highlights its dominant role in the optimization, driven by the region's structural simplicity and exposure to high loads. It consists solely of two spar-cap cores and two face-sheet layers, making it highly sensitive to stiffness adjustments.

Between the DD and DD-Local models, a distinct trend emerges: the **DD configuration achieves lower mass near the root** **while the DD-Local model performs slightly better toward the mid-span.** **DD-Local configuration achieves a lower mass**




Figure 16. Spanwise distribution of mass.

between the root and max. chord. This behavior reflects the additional flexibility of the DD-Local setup, which allows localized stiffness adaptation but yields only marginal overall improvement. Similarly, the

This is further evidenced by Figure 17: in the cylindrical root region, the DD-Local angles cluster around 37° , coinciding with the globally optimized DD solution. Since this region contributes the largest share of mass savings, it dominates the global optimum for the DD case — when a single angle pair is enforced across the entire blade, the optimizer converges to the value that minimizes mass in the most weight-critical zone. Beyond the root, where spars and reinforcements assume the primary load-bearing role, the DD-Local case adapts its angles to local structural demands and diverges from the one-angle solution.

Figure 17 shows that in the cylindrical root region, the DD-Local angles cluster around 37° , coinciding with the globally optimized DD solution. Since this region contributes the largest share of mass savings, it explains the global optimum for the DD case: a single angle pair enforced across the entire blade naturally converges to the value that is most beneficial in the most weight-critical zone. Beyond the root, where spars and reinforcements assume the primary load-bearing role, the DD-Local case adapts its angles to local structural demands, and the two solutions diverge. Nevertheless, 37° remains the most effective uniform configuration overall.

Given that the DD-Hard configuration shows limited gains relative to the triaxial baseline. As both variants primarily, it confirms that restricting $\Phi = 0^\circ$ leaves little room for stiffness tailoring. As DD-Hard and DD-Local serve as boundary references for the Double-Double formulation, the — the former a near-triaxial constraint, the latter an idealized stiffness benchmark — the following analysis focuses on comparing the Triax and DD cases as the most meaningful comparison.

5.1 Comparative Analysis of Triaxial and Double-Double-DD Configurations




Figure 17. Spanwise distribution of fiber angles for the DD-Local case.

To better interpret the influence of laminate architecture on the mass distribution, the thickness profiles provide a clear physical indication of how laminate architecture influences mass distribution. Figure 18 compares the spar-cap core and shell-skin thicknesses for the Triax and DD configurations. Near the root, within the cylindrical section, the $[0_2, \pm 45]$ layup exhibits consistently thicker components than the $[\pm 48, \pm 48]$ configuration: about 36.4% greater CFRP-core thickness and 9% greater GFRP-skin thickness in the first section. This highlights how the a 7% greater shell-skin thickness than the $[\pm 37, \pm 37]$ configuration. Conversely, the DD layup requires a 2%–6% greater spar-cap thickness through the transition region toward maximum chord. This trade-off highlights how laminate orientation affects not only its own stiffness but also the material demand in adjacent layers structural components.

After the cylindrical sections, the shell skin thickness shows a progressive loss of structural relevance, as spars and edge reinforcements assume the primary load-bearing function. A marked reduction occurs at the 6th section (6th step in Figure 18), limited by the tapering ratio 7.5. For the triaxial skin, the thickness decreases from 37.2 mm to 5.0–37.3 mm to 5.5 mm over the local span; for the DD configuration, it decreases from 31.7 mm to 4.2–32.7 mm to 8.2 mm, both matching the allowable slope. By the 79th section, both skins attain their minimum allowable thicknesses : of 2.0 mm for the Triax and 1.5 mm for the DD configuration, corresponding to four and three plies, respectively. The larger minimum thickness of the Triax skin results in locally higher bending stiffness, which slightly reduces the spar-cap demand but does not improve the overall mass efficiency of the section, as inferred from.

Given the relevance of the root section in terms of root section's significant mass contribution and the strong influence of DD angles, this region is analyzed in more detail. The stiffer the laminate is in the direction of load application, the greater the




Figure 18. Thickness distribution of spar cap and shell skin

expected concentration of membrane forces. This effect is evident in Figure 19, where axial loads N_x concentrate within the spar-cap region due to the thick unidirectional CFRP layers.

However, the triaxial laminates contain a larger portion of 0° plies, which concentrate excessive axial stiffness in the face sheets. Considering the superior strength-to-weight ratio of CFRP and the structural role of the spar cap, this behavior contradicts the most efficient stiffness distribution. As shown in Figure 20, the spar cap remains far from the constraint threshold of 0, while the shell operates at its limits under buckling criteria. Consequently, the optimizer first increases the spar-cap thickness to relieve part of the load carried by the shell, which acts as a sinking component. In addition, the 0° -dominated layup provides poor buckling resistance, further requiring local thickening of both the spar-cap core and shell face sheets. Conversely, the $[\pm 48, \pm 48]$ configuration, with its lower axial stiffness and improved buckling compliance, reduces the spar-cap demand for load redistribution and is inherently thinner.

~~summarizes the interaction between shell skins and spar-cap core, illustrating the feedback process responsible for the inferior structural response of the triaxial laminate in the root region.~~

~~Interaction between Triax skin and spar cap response.~~

In terms of trailing and leading edge reinforcements, as shown in Figure 21, they follow a similar overall trend for both the Triax and DD configurations. Reinforcements are generally thinner in the Triax case, primarily due to the additional axial




Figure 19. Axial force distribution (N_x) for the critical minimum edgewise moment case (Triax and DD).




Figure 20. Constraint contour distribution for the Triax case.

stiffness provided by the 0-degree plies in the skin. In contrast, the DD configuration lacks this axial reinforcement from the skin, and the UD core must compensate for this, resulting in thicker reinforcements.

The most pronounced differences occur at the beginning of the reinforcement regions, around the 6th section, where the Triax reinforcements start from lower thicknesses. This behavior results from the combination of tapering constraints and




Figure 21. Thickness distribution of TE and LE reinforcements




Figure 22. Flapwise (upper) and edgewise (lower) stiffness distributions for both configurations.

strength-driven sizing: the stiffer Triax skin, dominated by 0° plies, carries part of the axial load that would otherwise be absorbed by the reinforcements. Conversely, the softer DD skin ($\pm 48^\circ$) transfers greater axial demand to the cores, requiring locally thicker reinforcements. Beyond this zone, buckling becomes dominant, leading to a less pronounced thickness offset between configurations, as the triax contribution of 0-degree layers is less efficient.

550 Given the redistribution of loads between shell skins, spar-cap cores, and LE/TE reinforcements, spanwise variations in blade stiffness ~~are expected~~can occur. As shown in Figure 22, ~~the largest difference~~some minor change in flapwise stiffness occurs near the root, where the DD is softer due to its reduced spar-cap thickness. Beyond this region, the spar-cap thicknesses in both configurations converge, leading to similar stiffness trends along the remaining span. In contrast, the edgewise stiffness distribution exhibits a larger root-region offset, even though both configurations converge along the span. In edgewise bending, 555 the spar cap contributes less to stiffness, shifting the dominant role to the reinforcements and shell skins. The Triax skin, with its higher axial stiffness, therefore provides greater support, particularly at the root and near the tip where LE and TE reinforcements terminate. In these regions, the skin dominates the edgewise response.

5.2 In-Depth Analysis of the Optimized ~~Double-Double~~DD Blade

Near the root (Figure 23), the configuration reveals a structurally simple yet heavily reinforced section. The high material 560 density in this region reflects its critical role in load transfer, particularly through the spar cap and shell skin. The skin plays a dominant role in this area and benefits the most from optimization, as previously discussed.

Progressing outward, Figure 24 illustrates the transition in structural composition with the introduction of foam cores, UD Glass reinforcements, and the shear webs. Among the layups originating from the root, only the spar cap maintains the same thickness distribution trend. In contrast, the shell skin rapidly decreases in thickness and structural relevance, in line with the 565 shift toward spar- and reinforcement-dominated load paths. The foam core has its highest thickness value at 19 % of the span shown in Figure 25.

The section at 83 % span, shown in Figure 26 illustrate the increasingly simplified structural layout of the blade as it approaches the tip. The introduction of foam at the leading and trailing edges reflects a modification incorporated into the CRC-15 blade to enhance local bending stiffness in a region where the UD glass is already tapered out. Notably, the foam 570 cores are not reduced to their minimum allowable thickness, indicating their structural relevance in mass saving.

A key characteristic of the IEA-15-240 design is its material symmetry between the pressure and suction sides. Although the outer geometry is aerodynamically asymmetric, each ~~structural panel on the upper surface~~upper-surface structural panel has a mirrored counterpart on the lower ~~side~~surface. Under asymmetric operational loading, particularly flapwise bending, the suction side experiences higher compressive stresses and therefore ~~becomes~~buckling can become a critical factor in ~~design.~~ 575 ~~As widely reported in the literature (Ullah et al., 2020), this region is more susceptible to buckling, which typically governs the sizing of large wind turbine blades~~some areas, as reported in Ullah et al. (2020).

In the CRC simulations, the ~~suction-side panels govern the~~suction side governs structural sizing along the span due to the dominant compressive demand ~~imposed by~~from bending. The spar caps are constrained by the peak flapwise moment, while the leading and trailing edges are governed by combined flapwise–edgewise load cases. The leading edge is placed in compres-




Figure 23. Section at 1% span.




Figure 24. Section at 12% span.




Figure 25. [Section at 19% span.](#)




Figure 26. Section at 83% span.

580 sion under the 150-degree moment orientation, whereas the trailing edge is compressed under the 30-degree orientation, which reverses the tension–compression distribution between the two regions. ~~This loading pattern establishes compression-induced buckling as the~~

In the CRC simulations, the suction side governs structural sizing along the span due to the dominant compressive demand from bending. The spar caps are constrained by the peak flapwise moment, while the leading and trailing edges are governed
585 by combined flapwise–edgewise load cases. The leading edge is placed in compression under the 150° moment orientation, whereas the trailing edge is compressed under the 30° orientation, reversing the tension–compression distribution between the two regions.

Maximum strain is the primary sizing mechanism across ~~the suction-side panels, confirming that the DD configuration operates in the same regime~~ most of the suction side, with compression-induced buckling becoming critical on the quarter-cylindrical
590 shell at the leading edge and in some trailing edge panels toward the rear of the blade. The tailored ~~$\pm 48^\circ$ laminate angles align more effectively with the principal load paths~~ $\pm 37^\circ$ laminate finds a better compromise between these two failure modes than the triaxial layup, ~~whose higher axial stiffness interacts less efficiently with the~~ : by reducing axial stiffness in the skin, it redistributes load more effectively toward the spar caps and edge reinforcements, which are better suited to carry it.

6 Conclusions

595 This work introduced a multi-parametric panel approach and incorporated it into the blade-optimization workflow, enabling sandwich panels to be represented as modular assemblies with independently parameterized materials. The formulation was verified through stiffness, load-path, and tapering consistency tests, establishing its suitability for applying continuous composite descriptions. This capability enabled the examination of ~~Double-Double~~ DD laminates as viable replacements for conventional triaxial skins in a large-scale optimization setting.

600 ~~With this, the~~ The optimization of the CRC-15-240 blade using ~~Double-Double laminates~~ DD laminates on the shell resulted in a mass reduction of ~~8.84% , equivalent to 6,348.6 kg, 4% (2800 kg)~~ compared to the baseline triaxial configuration. ~~This improvement was achieved by replacing the original , achieved through the substitution of the~~ triaxial skins with ~~laminates based on a $[\pm 48^\circ / \pm 48^\circ]$ building block. The resulting configuration shifted a $[\pm 37^\circ / \pm 37^\circ]$ DD layup.~~

In general, 0° plies minimize spanwise strain while 45° plies maximize buckling resistance. The optimized $[\pm 37^\circ / \pm 37^\circ]$
605 configuration strikes a compromise between these two demands, shifting the skin response from an axially stiff regime to ~~toward~~ a softer one , better suited to resisting that better balances shear and buckling :-

~~Although 45° layers are generally optimal for such loading conditions, the optimized configuration converged toward slightly higher off-axis angles. Two main factors explain this tendency. First, the interaction between shear and compression loads benefits from stress redistribution within the layer matrix. Second, the solver implicitly sought to reduce flapwise bending stiffness, favoring higher off-axis orientations and maximizing the use of~~ resistance against strain limits. This also redistributes
610 axial stiffness from the shell to the spar caps and edge reinforcements, resulting in increased spar-cap thickness. In turn, the

optimizer maximizes the structural contribution of the unidirectional carbon fiber, which offers superior strength-to-weight performance in the flapwise direction.

Beyond the spar caps, the upper-skin-suction-side shell emerged as the dominant sizing region. This area experienced the highest stressesstress levels, particularly in compression, which were identified as the primary failure mode. ~~These trends align with the findings of Zerbst et al. (2025), who observed similar angle convergence in the upper panels of an aircraft wing optimized with Double-Double laminates. In both cases, the upper skins developed greater thicknesses and converged toward comparable orientations, reinforcing the physical plausibility of the simulated results.~~

From a stiffness perspective, the aeroelastic response was only moderately affected. The most significant variations occurred near the blade root, where local mass reductions reached approximately 6470%. Despite these changes, all flapwise and edge-wise displacements remained within the operational limits defined in Gaertner et al. (2020), confirming the structural viability of the optimized design.

From a manufacturing standpoint, the optimized Double-Double-DD skins integrate seamlessly into existing blade production practices. In a manner consistent with triaxial laminates, they can be assembled as repeating blocks, but with two selected fiber angles arranged according to the Double-Double-DD stacking pattern. This configuration remains fully compatible with current fabrics and vacuum-infusion processes and ~~does not introduce any~~ introduces no additional layup complexity. Consequently, the Double-Double-DD concept offers a practical approach to achieving weight savings while maintaining the established workflow used for conventional triaxial skins.

6.1 Future Work

~~Several~~Several additional research directions naturally extendarise from this work. ~~First, integrating a fully-coupled aeroelastic analysis into the optimization pipeline would enable more accurate prediction of stiffness-induced load redistribution. The current formulation assumes fixed aerodynamic loading and therefore does not capture secondary effects arising from skin softening or stiffness variation. While the present study focused on preliminary investigations of DD laminates as a novel structural concept, future studies can evaluate its performance with higher-fidelity models and analyses, creating a basis for subsequent detailed design stages:~~

~~Second, fatigue modeling~~

- Fatigue modeling is a key area for further work. ~~Double-Double~~ Although DD laminates are relatively new and lack extensive experimental data, ~~so~~ their long-term cyclic performance remains uncertain. Future research should integrate simplified fatigue degradation models into the optimization process and support experiments to characterize endurance. These data would allow direct fatigue constraints in the design space and, when needed, guide limits on allowable configurations. Nevertheless, preliminary tension–compression fatigue tests, such as those in Vasconcelos et al. (2025), indicate that Double-Double-DD laminates retain structural integrity under cyclic loading, supporting their long-term use.

- 645 – Matrix-dominated damage mechanisms could exhibit for the present DD case with $\pm 37^\circ$, since it lacks a third fiber orientation and is therefore not statically determined. A first study considering a constraint that enforces a minimum difference between the DD angles (here 30°) indicates a mass increase of $0.8t$ compared to the $\pm 37^\circ$ DD case, while still maintaining a $2t$ mass advantage over the triax configuration. Further research on double-double laminates is needed to better understand their susceptibility to matrix-dominated damage mechanisms.
- 650 – Through-thickness shear effects were incorporated into the buckling criterion in a simplified manner ($k = 1$, see subsection 4.4). A more rigorous treatment should adopt advanced lamination theories such as the First-Order Shear Deformation Theory (FSDT) or Mindlin–Reissner theory, which better capture shear deformation in thicker sandwich laminates. Additionally, the reference plane should be set to the mould surface rather than the mid-plane to improve the accuracy of the predicted bending stiffness.
- 655 – Higher fidelity strength criteria such as LaRC03 or Puck describe a physically based failure mechanism and capture specific mechanisms (e.g. matrix cracking).
- A fully coupled aeroelastic analysis integrated into the optimization pipeline would enable more accurate prediction of stiffness-induced load redistribution. The current formulation assumes fixed aerodynamic loading and therefore does not capture secondary effects arising from skin softening or stiffness variation.

Appendix A: Derivation of Plane-Shifted Stiffness Matrices

660 Extension Stiffness:

$$\begin{aligned}
 [\mathbf{A}^{\text{new}}] &= \sum_k [\bar{\mathbf{Q}}_k] [z_{k-1}^{\text{new}} - z_k^{\text{new}}] \\
 &= \sum_k [\bar{\mathbf{Q}}_k] [(z_{k-1}^0 - \Delta z) - (z_k^0 - \Delta z)] \\
 &= \underbrace{\sum_k [\bar{\mathbf{Q}}_k] [z_{k-1}^0 - z_k^0]}_{\mathbf{A}^0} \\
 &= [\mathbf{A}^0]
 \end{aligned}$$

Bending–Extension Stiffness:

$$\begin{aligned}
[\mathbf{B}^{\text{new}}] &= -\frac{1}{2} \sum_k [\bar{\mathbf{Q}}_k] [(z_{k-1}^{\text{new}})^2 - (z_k^{\text{new}})^2] \\
&= -\frac{1}{2} \sum_k [\bar{\mathbf{Q}}_k] [(z_{k-1}^0 - \Delta z)^2 - (z_k^0 - \Delta z)^2] \\
&= -\frac{1}{2} \sum_k [\bar{\mathbf{Q}}_k] [(z_{k-1}^0)^2 - 2z_{k-1}^0 \Delta z + \Delta z^2] \\
&\quad + \frac{1}{2} \sum_k [\bar{\mathbf{Q}}_k] [(z_k^0)^2 - 2z_k^0 \Delta z + \Delta z^2] \\
&= -\frac{1}{2} \sum_k [\bar{\mathbf{Q}}_k] [(z_{k-1}^0)^2 - (z_k^0)^2] \\
&\quad \underbrace{\hspace{10em}}_{\mathbf{B}^0} \\
&\quad + \Delta z \underbrace{\sum_k [\bar{\mathbf{Q}}_k] [z_{k-1}^0 - z_k^0]}_{\mathbf{A}^0} \\
&= [\mathbf{B}^0] + \Delta z [\mathbf{A}^0].
\end{aligned}$$

Bending Stiffness:

$$\begin{aligned}
[\mathbf{D}^{\text{new}}] &= \frac{1}{3} \sum_k [\bar{\mathbf{Q}}_k] [(z_{k-1}^{\text{new}})^3 - (z_k^{\text{new}})^3] \\
&= \frac{1}{3} \sum_k [\bar{\mathbf{Q}}_k] [(z_{k-1}^0 - \Delta z)^3 - (z_k^0 - \Delta z)^3] \\
&= \frac{1}{3} \sum_k [\bar{\mathbf{Q}}_k] \left\{ (z_{k-1}^0)^3 - 3\Delta z (z_{k-1}^0)^2 + 3\Delta z^2 z_{k-1}^0 \right. \\
&\quad \left. - \Delta z^3 - [(z_k^0)^3 - 3\Delta z (z_k^0)^2 + 3\Delta z^2 z_k^0 - \Delta z^3] \right\} \\
&= \frac{1}{3} \sum_k [\bar{\mathbf{Q}}_k] [(z_{k-1}^0)^3 - (z_k^0)^3] \\
&\quad \underbrace{\hspace{10em}}_{\mathbf{D}^0} \\
&\quad + 2\Delta z \underbrace{\left(-\frac{1}{2} \sum_k [\bar{\mathbf{Q}}_k] [(z_{k-1}^0)^2 - (z_k^0)^2] \right)}_{\mathbf{B}^0} \\
&\quad + \Delta z^2 \underbrace{\sum_k [\bar{\mathbf{Q}}_k] [z_{k-1}^0 - z_k^0]}_{\mathbf{A}^0} \\
&= [\mathbf{D}^0] + 2\Delta z [\mathbf{B}^0] + \Delta z^2 [\mathbf{A}^0].
\end{aligned}$$

List of abbreviations

AEP	Annual Energy Production. 1, 37
BB	Building Block. 1, 5, 37
CLT	Classical Laminate Theory. 1, 5, 37
DD	Double-Double. 1, 3–11, 21–23, 26, 27, 31, 34–37
DD-Hard	DD laminate with fixed 0° , and Ψ variable. 1, 37
DD-Local	DD laminate with individualized set of angles per cross-section. 1, 37
IEA	Internation Energy Agency. 1–3, 37
RWT	Reference Wind Turbine. 1, 2, 37
Triax	DD laminate with fixed 0° , 45° angles. 1, 37
UD	Unidirectional. 1, 9, 37

List of symbols

G_c	Shear modulus of the sandwich core. 1, 37
$N_{x,cr}, N_{xy,cr}$	Critical buckling load for compression and shear. 1, 37
R	Ration between applied and critical load for the related mode. 1, 37
T	Total stack, following the Nettles convention (Nettles, 1994). 1, 5, 37
$TSAI$	Tsai modulus is the trace of the ply stiffness matrix ($TSAI = \text{Tr}[Q]$). 1, 37
V_x^A, V_x^B, V_x^D	Lamination parameters in accordance with (Zerbst et al., 2025). 1, 7, 37

W_x	Trigonometric functions of the ply angle θ_k . 1, 7, 37
$[\mathbf{A}]$	Extensional stiffness matrix. 1, 5, 37
$[\mathbf{B}^*]$	Coupling stiffness matrix normed by the laminate thickness. 1, 5, 37
$[\mathbf{D}]$	Bending stiffness matrix. 1, 5, 37
$[\mathbf{Q}]$	Ply stiffness matrix. 1, 6, 37
Φ	First double-double angle. 1, 5, 37
Ψ	Second double-double angle. 1, 5, 37
α	Fraction of the Tsai modulus. 1, 37
ϕ	First double-double angle. 1, 37
ψ	Second double-double angle. 1, 37
ρ	Density. 1, 37
σ_1	Normal stress. 1, 37
σ_2	Transverse normal stress. 1, 9, 37
τ_{12}	Shear stress. 1, 9, 37
θ	Ply angle orientation. 1, 7, 37
$\tilde{D}_{11}$	Effective bending stiffness term of the laminate. 1, 21, 37
b	Buckling/panel width. 1, 37
g	Constraint e.g. for stability, strength etc.. 1, 37
k	Shear correction factor. 1, 37
kx and ks	Buckling coefficients for compression and shear according to (Structural Analysis Working Group I, 2009). 1, 21, 37
m	Mass of.... 1, 37
n_x	Uniaxial load. 1, 9, 37
n_{xy}	Shear load. 1, 9, 37
r	Number of repeats. 1, 5, 37
t_c	Thickness of the sandwich core. 1, 37
t_{lam}	Thickness of the laminate. 1, 6, 37
z_k	Distance of the k -th ply to the laminate mid-plane. 1, 7, 37

Data availability. The raw data required to reproduce these findings are available under the following repository:
670 <https://doi.org/10.5281/zenodo.17965770> (Werthen, 2025).

Author contributions. EW and GNR developed the methodology and software code, did the analyses and wrote the manuscript. SD and LT supported the implementation of the approach into the *lightworks* framework. DZ and CH revised the manuscript and provided scientific supervision.

Competing interests. The authors declare that they have no known competing financial interests or personal relationships that could have
675 appeared to influence the work reported in this paper.

Acknowledgements. We would like to acknowledge the funding by the Deutsche Forschungsgemeinschaft (DFG, German Research Foundation) under Germany's Collaborative Research Center – CRC 1463/2 - Integrated design and operation methodology for offshore megas-
tructures – Project-ID 434502799.

References

- 680 Almeida, J. H. S., Balonek, E., and Castro, S. G.: Beyond Double-Double theory: n-Directional stacking sequence optimisation in composite laminates, *Composite Structures*, 373, 119 586, <https://doi.org/https://doi.org/10.1016/j.compstruct.2025.119586>, 2025.
- Amabili, M.: *Composite, Sandwich and Functionally Graded Materials: Advanced Nonlinear Shell Theories*, p. 90–123, Cambridge University Press, 2018.
- Bak, C., Zahle, F., Bitsche, R., Kim, T., Yde, A., Henriksen, L., Hansen, M., Blasques, J., Gaunaa, M., and Natarajan, A.: The DTU 10-MW
685 Reference Wind Turbine, danish Wind Power Research 2013 ; Conference date: 27-05-2013 Through 28-05-2013, 2013.
- Bortolotti, P., Tarrés, H., Dykes, K., Merz, K., Sethuraman, L., Verelst, D., and Zahle, F.: IEA Wind TCP Task 37: Systems Engineering in Wind Energy-WP2.1 Reference Wind Turbines, National Renewable Energy Laboratory (NREL), <https://doi.org/10.2172/1529216>, 2019.
- Bortolotti, P., Bay, C., Barter, G., Gaertner, E., Dykes, K., McWilliam, M., Friis-Moller, M., Pedersen, M. M., and Zahle, F.: *System Modeling Frameworks for Wind Turbines and Plants: Review and Requirements Specifications*, Tech. rep., <https://doi.org/10.2172/1868328>, 2022.
- 690 Camarena, E., Anderson, E., Paquette, J., Bortolotti, P., Feil, R., and Johnson, N.: Land-based wind turbines with flexible rail-transportable blades – Part 2: 3D finite element design optimization of the rotor blades, *Wind Energy Science*, 7, 19–35, <https://doi.org/10.5194/wes-7-19-2022>, 2022.
- Castro, O.: Fatigue strength of composite wind turbine blade structures, Ph.D. thesis, Denmark, <https://doi.org/10.11581/00000037>, 2018.
- Couto, L. d. L., Moreira, N. E., Saito, J. Y. d. O., Hallak, P. H., and Lemonge, A. C. d. C.: Multi-Objective Structural Opti-
695 mization of a Composite Wind Turbine Blade Considering Natural Frequencies of Vibration and Global Stability, *Energies*, 16, <https://doi.org/10.3390/en16083363>, 2023.
- Dähne, S., Werthen, E., Zerbst, D., Tönjes, L., Traub, H., and Hühne, C.: Lightworks, a scientific research framework for the design of stiffened composite-panel structures using gradient-based optimization, *Structural and Multidisciplinary Optimization*, 67, 70, <https://doi.org/10.1007/s00158-024-03783-1>, 2024.
- 700 Daniel, I., Werner, B., and Fenner, J.: Strain-rate-dependent failure criteria for composites, *Composites Science and Technology*, 71, 357–364, <https://doi.org/https://doi.org/10.1016/j.compscitech.2010.11.028>, 2011.
- DNV GL: DNVGL-ST-0376: Rotor Blades for Wind Turbines, Standard, Proposal No. 2015-218, Final Draft for Hearing, published by DNV GL Renewables Certification, 2015a.
- DNV GL: DNVGL-ST-0376: Rotor blades for wind turbines, Standard, DNV GL AS, Høvik, Norway, <https://rules.dnv.com>, 2015b.
- 705 Gaertner, E., Rinker, J., Sethuraman, L., Zahle, F., Anderson, B., Barter, G., Abbas, N., Meng, F., Bortolotti, P., Skrzypinski, W., Scott, G., Feil, R., Bredmose, H., Dykes, K., Sheilds, M., Allen, C., and Viselli, A.: Definition of the IEA 15-Megawatt Offshore Reference Wind Turbine, Tech. rep., International Energy Agency, <https://www.nrel.gov/docs/fy20osti/75698.pdf>, 2020.
- Garofano, A., Sellitto, A., Acanfora, V., Di Caprio, F., and Riccio, A.: On the effectiveness of double-double design on crashworthiness of fuselage barrel, *Aerospace Science and Technology*, 140, 108 479, <https://doi.org/https://doi.org/10.1016/j.ast.2023.108479>, 2023.
- 710 Gasch, R. and Tvele, J.: *Wind Power Plants: Fundamentals, Design, Construction and Operation*, Springer Berlin Heidelberg, Berlin, Heidelberg, 2nd ed. 2012 edn., ISBN 978-3-642-22937-4, 2012.
- Hayat, K., Siddique, S., Sultan, T., Ali, H. T., Aloufi, F. A., and Halawani, R. F.: Effect of Spar Design Optimization on the Mass and Cost of a Large-Scale Composite Wind Turbine Blade, *Energies*, 15, <https://doi.org/10.3390/en15155612>, 2022.

- Jung, S. and Nagaraj, V. T.: Structural Behavior of Thin- and Thick-Walled Composite Blades with Multi-Cell Sections, in: 43rd AIAA/AS-
 715 ME/ASCE/AHS/ASC Structures, Structural Dynamics, and Materials Conference, American Institute of Aeronautics and Astronautics,
<https://doi.org/10.2514/6.2002-1432>, structures, Structural Dynamics, and Materials and Co-located Conferences, 2002.
- Kappel, E.: Double–Double laminates for aerospace applications — Finding best laminates for given load sets, Composites Part C: Open
 Access, 8, 100 244, <https://doi.org/https://doi.org/10.1016/j.jcomc.2022.100244>, 2022.
- Kappel, E.: On invariant combinations of Qij coefficients and a novel invariant IQ, Composites Part C: Open Access, 10, 100 335,
 720 <https://doi.org/https://doi.org/10.1016/j.jcomc.2022.100335>, 2023.
- Kappel, E. and Tsai, S. W.: Double-Double Laminates - A Review on the Status Quo in Spring 2024, Tech. rep., DLR (German Aerospace
 Center), <https://elib.dlr.de/204753/>, published under Clean Aviation, UpWing, 2024.
- Kappel, E., Boose, Y., and Mißbach, M.: A CAI study on transition zones of conventional and Double-Double laminates, Composites Part
 C: Open Access, 14, 100 450, <https://doi.org/https://doi.org/10.1016/j.jcomc.2024.100450>, 2024.
- 725 Kassapoglou, C.: Design and Analysis of Composite Structures, <https://doi.org/10.1002/9781118536933>, 2013.
- Liu, P. and Barlow, C. Y.: Wind turbine blade waste in 2050, Waste Management, 62, 229–240,
<https://doi.org/https://doi.org/10.1016/j.wasman.2017.02.007>, 2017.
- Mishnaevsky, L., Branner, K., Petersen, H. N., Beauson, J., McGugan, M., and Sørensen, B. F.: Materials for Wind Turbine Blades: An
 Overview, Materials, 10, <https://doi.org/10.3390/ma10111285>, 2017.
- 730 Nettles, A. T.: Basic mechanics of laminated composite plates, Tech. rep., National Aeronautics and Space Administration, Huntsville, AL
 (United States). George C. Marshall Space Flight Center, <https://www.osti.gov/biblio/6880327>, 1994.
- Peters, R. W.: Buckling of Long Square Tubes in Combined Compression and Torsion and Comparison with Flat-plate Buckling Theories,
 Technical Note NACA-TN-3184, National Advisory Committee for Aeronautics (NACA), <https://ntrs.nasa.gov/citations/19930083964>,
 public domain. Work of the U.S. Government. Public use permitted, 1954.
- 735 Riccio, A., Caprio, F. D., Tsai, S., Russo, A., and Sellitto, A.: Optimization of composite aeronautical components by Re-designing with
 double-double laminates, Aerospace Science and Technology, 151, 109 304, <https://doi.org/https://doi.org/10.1016/j.ast.2024.109304>,
 2024.
- Rinker, J. and Dykes, K. L.: WindPACT Reference Wind Turbines, Tech. rep., National Renewable Energy Laboratory (NREL), Golden, CO
 (United States), <https://doi.org/10.2172/1432194>, 2018.
- 740 Rinker, J., Gaertner, E., Zahle, F., Skrzypiński, W., Abbas, N., Bredmose, H., Barter, G., and Dykes, K.: Comparison of loads from
 HAWC2 and OpenFAST for the IEA Wind 15 MW Reference Wind Turbine, Journal of Physics: Conference Series, 1618, 052 052,
<https://doi.org/10.1088/1742-6596/1618/5/052052>, 2020.
- Rosemeier, M. and Krimmer, A.: Rotorblattstruktur, in: Einführung in die Windenergietechnik, edited by Schaffarczyk, A. P., chap. 5, pp.
 169–220, Carl Hanser Verlag GmbH & Co. KG, 3 edn., ISBN 9783446473225, <https://doi.org/10.1007/978-3-446-47322-5>, 2022.
- 745 Samborsky, D. D. and Mandell, J. F.: Fatigue resistant fiberglass laminates for wind turbine blades, American Society of Mechanical Engi-
 neers, New York, NY (United States), <https://www.osti.gov/biblio/372115>, 1996.
- Scott, S., Greaves, P., Macquart, T., and Pirrera, A.: Comparison of blade optimisation strategies for the IEA 15MW reference turbine, Journal
 of Physics: Conference Series, 2265, 032 029, <https://doi.org/10.1088/1742-6596/2265/3/032029>, 2022.
- Serafeim, G. P., Manolas, D. I., Riziotis, V. A., Chaviaropoulos, P. K., and Saravanos, D. A.: Optimized blade mass reduction of a 10MW-
 750 scale wind turbine via combined application of passive control techniques based on flap-edge and bend-twist coupling effects, Journal of
 Wind Engineering and Industrial Aerodynamics, 225, 105 002, <https://doi.org/https://doi.org/10.1016/j.jweia.2022.105002>, 2022.

- Sjølund, J. H. and Lund, E.: Structural Gradient-Based Sizing Optimization of Wind Turbine Blades with Fixed Outer Geometry, Composite Structures, 203, 725–739, <https://doi.org/10.1016/j.compstruct.2018.07.031>, 2018.
- 755 Structural Analysis Working Group I: Luftfahrttechnisches Handbuch für Strukturberechnung (HSB), IASB (Industrie Ausschuss Struktur Berechnungsunterlagen), DASA-Airbus, Bremen, available in German and English at the Technical Information Library (TIB), Hannover, 2009.
- Tsai, S. and Melo, J.: Composite Materials Design and Testing: Unlocking Mystery with Invariants, Stanford Aeronautics & Astronautics, ISBN 9780986084515, <https://books.google.de/books?id=pLxsrgEACAAJ>, 2015a.
- 760 Tsai, S. and Melo, J.: Composite Materials Design and Testing: Unlocking Mystery with Invariants, Stanford Aeronautics & Astronautics, ISBN 9780986084508, <https://books.google.com.br/books?id=ykBrrgEACAAJ>, 2015b.
- Tsai, S. W.: Double–Double: New Family of Composite Laminates, AIAA Journal, 59, 4293–4305, <https://doi.org/10.2514/1.J060659>, 2021.
- Ullah, H., Ullah, B., and Silberschmidt, V. V.: Structural integrity analysis and damage assessment of a long composite wind turbine blade under extreme loading, Composite Structures, 246, 112 426, <https://doi.org/https://doi.org/10.1016/j.compstruct.2020.112426>, 2020.
- 765 Vasconcelos, T. B., Alves, J. L. C., da Costa Ferreira, E. P., Júnior, R. C. S. F., and Melo, J. D. D.: Static and fatigue behavior of double-double glass/epoxy laminates, Journal of Composite Materials, 59, 119–133, <https://doi.org/10.1177/00219983241261065>, 2025.
- VDI: Faserverbundwerkstoffe: Berechnung und Anwendung von Faserverbundstrukturen, <https://www.vdi.de/>, 1. Auflage, VDI Verlag, 2014.
- Werthen, E.: CRC1463 Blade designs with double-double laminates for the CRC15-240 turbine, <https://doi.org/10.5281/zenodo.17965770>, 2025.
- 770 Werthen, E., Ribnitzky, D., Zerbst, D., Kühn, M., and Hühne, C.: Aero-structural coupled optimization of a rotor blade for an upscaled 25 MW reference wind turbine, Journal of Physics: Conference Series, 2626, 012 012, <https://doi.org/10.1088/1742-6596/2626/1/012012>, 2023.
- Werthen, E., Hardt, D., Balzani, C., and Hühne, C.: Comparison of different cross-sectional approaches for the structural design and optimization of composite wind turbine blades based on beam models, Wind Energy Science, 9, 1465–1481, <https://doi.org/10.5194/wes-9-1465-2024>, 2024.
- 775 Zahle, F., Barlas, A., Lønbæk, K., Bortolotti, P., Zalkind, D., Wang, L., Labuschagne, C., Sethuraman, L., and Barter, G.: Definition of the IEA Wind 22-Megawatt Offshore Reference Wind Turbine, Tech. Rep. DTU Wind Report E-0243, <https://doi.org/10.11581/DTU.00000317>, Technical University of Denmark, International Energy Agency, ISBN 978-87-87335-71-3, 2024.
- Zerbst, D., Tönjes, L., Dähne, S., Werthen, E., Kappel, E., and Hühne, C.: Equivalent plate formulation of Double–Double laminates for the gradient-based design optimization of composite structures, Composite Structures, 354, 118 786, <https://doi.org/https://doi.org/10.1016/j.compstruct.2024.118786>, 2025.
- 780 Zhao, K., Kennedy, D., Miravete, A., Tsai, S. W., Featherston, C. A., and Liu, X.: Defining the Design Space for Double–Double Laminates by Considering Homogenization Criterion, AIAA Journal, 61, 3190–3203, <https://doi.org/10.2514/1.J062639>, 2023.